



CARLISLE'S **SURE-WHITE® PRESSURE-SENSITIVE MOLDED WALKWAY PADS**



Overview

Let Carlisle simplify your next Sure-White EPDM installation with their Pressure-Sensitive Walkway Pads. The Carlisle Walkway Pad is designed to protect the membrane in those areas exposed to repetitive foot traffic.

Intended Uses

- Walkways must be installed at all traffic concentration points (i.e., roof hatches, access doors, rooftop ladders, etc.) regardless of traffic frequency.
- Walkways must also be installed if regular maintenance (once a month or more) is necessary to service rooftop equipment.

Features and Benefits

- Excellent tear and puncture resistance
- UV resistant
- Slip resistant

Installation*

- Remove excess dust and dirt from the membrane by wiping with a clean rag. To remove accumulated dirt, footprints, etc., scrub the membrane sheets with warm low-sudsing soap and water and rinse with clean water.

- Clean the dry membrane surface by scrubbing with HP Splice Wipes or clean natural fiber rags using Weathered Membrane Cleaner. Use Carlisle EPDM Primer to prime Sure-Seal or Sure-White EPDM Membrane when adhering pads.
 - Adhere Walkway Pads using Carlisle EPDM Primer. Apply primer to deck surface where tape will contact deck surface.
 - Allow a 1" (25 mm) wide break between Walkway Pads. Discontinue Walkways over field splices allowing a minimum 1" (25 mm) gap.
- * REVIEW CURRENT CARLISLE SPECIFICATIONS AND DETAILS FOR SPECIFIC APPLICATION REQUIREMENTS.

Precautions

The product is to be used as a walkway only and is not designed as a substitute for ballast. Walkway Pads cannot be installed within 10' (3 m) of the roof perimeter or on projects which exceed 50' (15 m) in height for Design "B" systems. Concrete pavers may be used in these areas. When installing walkways in conjunction with ballast, avoid the entrapment of small ballast below walkways. Walkway Pads are a maintenance item and are not covered under the Carlisle membrane systems warranty.

Sure-White PS Molded Walkway Pads

Typical Properties and Characteristics

Color	White
Pad Thickness	min - .162 max - .202
Performance Requirements	
Density, pct	70
Tensile Strength, psi ASTM D412 Unaged	500
Tear Resistance, ppi ASTM D624 Unaged	250
Packaging	30 inches x 30 inches - 50 per skid (76 cm x 76 cm)